

Technical Data

FIRE SEALANT 400

Fire and Acoustic Rated Low Modulus Sealant



Description

FIRE SEALANT 400 is a neutral cure, elastic silicone sealant which has a fire rating of up to 4 hours in certain joint configurations (when tested to BS EN 1366-4 2006).

Benefits

- Fire rated to BS EN 1366-4 2006
- Neutral cure – adheres to most building surfaces, porous and non porous
- Permanently flexible (25% movement accommodation)
- Excellent weathering characteristics – suitable for internal and external use.
- Can be used in joints up to 50mm wide.
- No priming required for most construction substrates
- Non slump - easy to apply and tool off
- Forms an acoustic seal

Recommended For

All building and glazing joints which require a fire rating.

Sealing joints, voids and irregular holes in fire walls, partitions and other structures; also for maintaining the integrity of pipes and cables that penetrate them. Ideal for use for fire rated expansion joints.

Specification Compliances

- Fire rated BS EN 1366-4 2006 (report no. 181970 (May 2009) DIN 4102 -B1 and EN1366 Part 4.
- Acoustic tested to BS EN ISO 140-3:1995.
- Tested for air permeability to EN 13141-1 Ventilation for buildings. Performance testing of components/products for residential ventilation.
- ISO11600 F 25LM when tested to ISO9047. (Report number RLR.12).



Available in

380ml Cartridges in the following colours:

- White
- Grey
- Black

Storage

Store in cool dry conditions between + 5°C and 25°C.

Shelf Life

Use within 12 months.

Technical Data

FIRE SEALANT 400

Fire Rated Low Modulus Sealant

Health & Safety

Consult MSDS for full list of hazards.

Joint Dimensions

For maximum movement accommodation, it is recommended that:

1. The sealant joint depth should be no less than 5mm
2. Joint depth should be 5mm for joints up to 10mm wide
3. Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints

Joint depth may be adjusted to the correct size using EVERBUILD JOINT BACKER ROD or BOND BREAKING TAPE in cases where there is not sufficient depth to use Backer Rod.

Joint Width Calculation

Joint widths are calculated as in BS6213:

$$\text{Width} = \frac{M \times 100}{F} + M$$

Where M = movement and F = movement accommodation Factor

Specific Data

Slump	Nil in joints up to 50mm
Max Joint Width	50mm *
Hardness	Shore A: 35 - 40
SG	1.29g/cm ³
Tack Free Time	20 Minutes
Joint Movement	+ / - 25% of Original Size
Cure Rate	1mm / 24hrs at 50% Relative Humidity 23°C
Service Temperatures	-40 - +140°C
Cleaning	Uncured: white spirits; cured sealant: SILICONE EATER
Life Expectancy	25 Years +

* For larger joint configuration please consult our technical services

Surface Preparation

All surfaces must be clean, dry and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application.

Movement Factors

Butt joints: 50% (not to exceed +/- 25% in any one direction)

Lap joints: 100% (not to exceed +/- 50% in any one direction)

Primer

Mortar: Use Primer P1.

Improve adhesion on non-porous surfaces by using Primer NP2.

Specific Resistances

Mild acids / alkali's at room temperature < 10% concentration.

Limitations

- Do not use on surfaces that bleed oils or plasticisers or in contact with bitumen or asphalt.
- Do not attempt to sand down. Finish smooth as per directions.
- Not overpaintable.

Fire Rating Table (BS476) Part 20 1987

WALL DEPTH (MM)	SEALANT	GAP WIDTH (MM)	SEALANT DEPTH (MM)	BACKING ROD	INTEGRITY (MINS)	INSULATION (MINS)
200	Fire Sealant 400	11	10	15mm diameter polyethylene	240	240
200	Fire Sealant 400	31	20	40mm diameter polyethylene	225	240
100	Fire Sealant 400	33	20	40mm diameter polyethylene	116	187
100	Fire Sealant 400	11	10	15mm diameter polyethylene	146	202

NOTE: FIRE SEALANT 400 seals applied flush with BOTH faces of wall using two separate backing blocks.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.